

# Highly Refined Base Oils

## ► Base Oil 60N

Test Items	Test Method	Specification	Test Result
Density, (kg/m <sup>3</sup> 15 °C)	ASTM D 4052	Report	850.1
Flash Point (°C)	ASTM D 93	160 min	172.0
Distillation	ASTM D 86		
IBP (°C)		315 ± 5	315
FBP(°C)		355 ± 5	352
Corrosion, Copper Strip (3hr 50 °C)	ASTM D 130	1 max	1a
Aniline Point (°C)	ASTM D 611	Report	94.3
Sulfur (mg/kg)	ASTM D 5453	1 max	0.1
Aromatics (wt %)	UOP495	Report	L0.01
Color (Saybolt)	ASTM D 156	30 min	+30
Viscosity, at 40°C, (mm <sup>2</sup> /s)	ASTM D 445	Report	8.175
Pour Point, °C	ASTM D 97	-35 min	L-40

